



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649 • Stow, Ohio 44224-064
Phone (330) 928-5188 • Fax (330) 928-0013
www.struktol.com • customerservice@struktol.com

TECHNICAL DATA

STRUKTOL[®] 40 MS **HOMOGENIZING AGENT**

COMPOSITION

Complex mixture of aromatic and aliphatic hydrocarbon resins.

TYPICAL PROPERTIES

Appearance	Bluish to brown pastilles
Ash Content (% , max.)	2
Softening Point (°C)	96 – 106*
Specific Gravity (g/cm ³)	1.06
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under the following storage conditions: It is recommended that material not be stored at temperatures above 95°F. Care must be taken not to double stack since the additional pressure will cause storage stability problems.
Packaging	25 kg. PE bags

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] 40 MS improves the homogeneity of elastomers of different polarity and viscosity. It is rapidly absorbed by the polymers during the mixing cycle. A relatively low viscosity mass is quickly achieved into which other compounding ingredients can easily be incorporated. The homogenizing agents are particularly effective with those elastomer blends which tend to crumble at the beginning of the mixing cycle. In most cases 40 MS is added along with the polymers in the mixing cycle.

The reduction of compound viscosity and "nerve" achieved with STRUKTOL[®] 40 MS assists downstream processing. For instance, bagging tendency can be reduced, extrusion rates are increased without increasing die swell, and calendaring properties are improved. These benefits are retained even after long storage periods of the green compound.

STRUKTOL[®] 40 MS increases the green tack of many compounds although strictly it is not a tackifier. It does, however, boost the efficiency of other tackifying agents.

STRUKTOL[®] 40 MS does not harden during vulcanization. The hardness of the vulcanizate is not reduced as much as when using, for example, mineral oil plasticizers.

Because of its color, STRUKTOL[®] 40 MS is not suitable for light colored compounds. Staining may occur under certain conditions. Where non-staining is specified, STRUKTOL[®] RP 28 should be used.

STRUKTOL[®] 40 MS has good solubility in aromatic and chlorinated hydrocarbon oils.

**After several months of storage the morphology of the product can slightly change. A softening point increase within the range of several degrees is typical.*

DOSAGE

4 - 15 phr

(03/10/2016)KAB/rca

The information herein is believed to be reliable, but is presented without guarantee or warranty, express or implied. Nothing contained herein is to be construed as a recommendation for any use which is in violation of an existing patent.