



STRUKTOL[®] RP 37

PROCESSING ADDITIVE

COMPOSITION

Proprietary blend of fatty acid derivatives.

PROPERTIES	TYPICAL VALUES
Appearance	White to off-white pastille
Dropping Point (°C)	53 - 63
Specific Gravity	1.03
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions.
Packaging	50 lb. bag

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] RP 37 is designed to act as a processing aid and mold release used in polypropylene to modify viscosity. It is used to provide a very large increase in product melt flow index. Excellent for use when contamination from polyethylenes or other polyolefins is present.

STRUKTOL[®] RP 37 is also very useful in recycling applications.

DOSAGE

0.1 – 2%