



# Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649  
Stow, Ohio 44224-0649 • www.struktol.com  
Phone (330) 928-5188 • Fax (330) 928-8726

# TECHNICAL DATA

## STRUKTOL® SA 0720

LUBRICANT ADDITIVE FOR PVC AND POLYMER PROCESSING

### COMPOSITION

Blend of mineral additives in a polymer carrier.

### TYPICAL PROPERTIES

Appearance	White to off-white pastille
Melting Point (°C)	80 - 100
Ash Content (% , max)	60
Specific Gravity	1.22
Physiological Behavior	Refer to safety data sheet
Storage Stability	Unlimited under normal storage conditions
Packaging	165 lb. drum

### RECOMMENDATIONS FOR APPLICATION

STRUKTOL® SA 0720 is a matting agent for rigid PVC to produce a matted/textured surface. It is ideal for water channeling applications or wherever a matted/textured surface on extruded or calendered rigid PVC products is desirable.

### DOSAGE

To be used at 0.5 – 3.0% by weight of total compound.

### FDA STATUS

STRUKTOL® SA 0720 is sanctioned for use by the Food and Drug Administration (FDA) in a number of applications, listed in the following sections of Title 21 of the Code of Federal Regulations:

175.105	177.1200	177.2800
175.210	177.1210	178.1005
175.300	177.1350	179.45
176.180	177.1390	181.30

(06/28/10)JMB/rca