



## Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649 • Stow, Ohio 44224-064  
Phone (330) 928-5188 • Fax (330) 928-0013  
www.struktol.com • customerservice@struktol.com

# TECHNICAL DATA

## **STRUKTOL<sup>®</sup> TPW 104** *PROCESSING ADDITIVE*

### **COMPOSITION**

Blend of an aliphatic carboxylic acid salts and mono and diamides.

<b><i>PROPERTIES</i></b>	<b><i>TYPICAL VALUES</i></b>
Appearance	Off-white to light tan beads, pastilles or powder
Dropping Point (°C)	95 - 115
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. bag (standard)

### **RECOMMENDATIONS FOR APPLICATION**

STRUKTOL<sup>®</sup> TPW104 is a unique blend of lubricants designed specifically for wood fiber/flour filled polyolefins. This product will provide improved surface quality, increased output rates and a wider processing window leading to overall improved processability.

STRUKTOL<sup>®</sup> TPW 104 can also be used in other polyolefin compounds where improved processability or output rates are required.

### **DOSAGE**

Typical usage levels are 2 – 6% of total compound weight.

(04/28/2016)MSF/rca

The information herein is believed to be reliable, but is presented without guarantee or warranty, express or implied. Nothing contained herein is to be construed as a recommendation for any use which is in violation of an existing patent.