



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649
Stow, Ohio 44224-0649 • www.struktol.com
Phone (330) 928-5188 • Fax (330) 928-8726

TECHNICAL DATA

STRUKTOL[®] TPW 113

PROCESSING ADDITIVE

COMPOSITION

Blend of complex, modified fatty acid ester

PROPERTIES

Appearance	Pastille or powder
Dropping Point (°C)	70 - 88
Specific Gravity	1.005
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. bag

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] TPW 113 is a functional lubricant package designed to provide superior filler wetting and dispersion characteristics in a wide range of polymer systems. This product has been engineered to provide significant processing improvements and output rate increases for filled compounds.

STRUKTOL[®] TPW 113 is recommended for wood-filled polyolefins where improved filler dispersion and surface quality is required.

DOSAGE

1 – 6% of total compound weight depending on filler loading and process requirements.

(03/14/2013)SNK/DAB/rca

The information herein is believed to be reliable, but is presented without guarantee or warranty, express or implied. Nothing contained herein is to be construed as a recommendation for any use which is in violation of an existing patent.