



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649
Stow, Ohio 44224-0649 • www.struktol.com
Phone (330) 928-5188 • Fax (330) 928-8726

TECHNICAL DATA

STRUKTOL[®] TPW 707 *PROCESSING ADDITIVE*

COMPOSITION

Proprietary blend.

TYPICAL PROPERTIES

Appearance	Beige pastille
Dropping Point (°C)	135 - 144
Specific Gravity	0.99
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions
Packaging	2000 lb. SS

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] TPW 707 is a functional lubricant blend that offers superior filler wetting and processing characteristics in various polymer systems.

DOSAGE

1 to 5% of total compound weight depending on filler loading and type.

(09/05/2013)GH/NK/rca