



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649 • Stow, Ohio 44224-064
Phone (330) 928-5188 • Fax (330) 928-0013
www.struktol.com • customerservice@struktol.com

TECHNICAL DATA

STRUKTOL[®] TR 219

BLENDING AID COMPATIBILIZER WITH PROCESSING LUBRICANT

COMPOSITION

Proprietary blend.

PROPERTIES	TYPICAL VALUES
Appearance	Light yellow pastille or powder
Dropping point (°C)	105 - 120
Specific Gravity	1.07
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. Bag

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] TR 219 is a blend of compatibilizer and processing lubricant that was designed for use in Nylon 6 and 6,6 compounds. The compatibilizer makes it effective at binding filler materials to the polymer system by virtue of its adhesive nature while the lubricant part provides improved processing characteristics of filled and unfilled polyamides. Typical improvements in processing are improved mixing and reduced die build-up (“die bearding”) and die drool. For injection molding applications, processors can expect to see better flow and mold filling vs. typical lubricants such as metallic stearates, montan waxes or amide waxes.

STRUKTOL[®] TR 219 is for use in nylon 6 and 6,6 compounds; both virgin and recycled. It has also been found to be effective in polyester (PET and PBT) compounds, especially recycled or recyclate-containing applications or in cases where the polyester compound is contaminated with other plastics.

DOSAGE

1.0 – 4.0%

(07/09/2015)JMB/rca

The information herein is believed to be reliable, but is presented without guarantee or warranty, express or implied. Nothing contained herein is to be construed as a recommendation for any use which is in violation of an existing patent.