



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649
Stow, Ohio 44224-0649 • www.struktol.com
Phone (330) 928-5188 • Fax (330) 928-8726

TECHNICAL DATA

STRUKTOL[®] TR 251 **PROCESSING AGENT**

COMPOSITION

A complex oleochemical mixture containing mono and di amides and metal soap.

PROPERTIES

Appearance	Beige pastille or prill
Dropping Point (°C)	115 - 125
Specific Gravity	.996
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. bag 165 lb. drum (prill only)

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] TR 251 is a unique blend of anionic and ionic surfactants with lubricant designed for processing EPDM and EVA. STRUKTOL[®] TR 251 improves dispersion of fillers, improves flow properties, promotes release and effectively acts to improve overall processing.

ADDITION LEVELS

EPDM 3 %
EVA 3 %

(01/22/08)CJR/mmm

The information herein is believed to be reliable, but is presented without guarantee or warranty, express or implied. Nothing contained herein is to be construed as a recommendation for any use which is in violation of an existing patent.