



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649 • Stow, Ohio 44224-064
Phone (330) 928-5188 • Fax (330) 928-0013
www.struktol.com • customerservice@struktol.com

TECHNICAL DATA

STRUKTOL® TR EBS

**BLENDING AID
PROCESSING ADDITIVE**

COMPOSITION

N,N' Ethylene Bis-stearamide

PROPERTIES

TYPICAL VALUES

Appearance	White bead or pastille
Acid Value	< 10
Melting Point (°C)	135 - 150
Specific Gravity	0.98
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. PE bags

RECOMMENDATIONS FOR APPLICATION

STRUKTOL® TR EBS is an exceptionally effective dispersion aid for a wide range of organic and inorganic pigments. STRUKTOL® TR EBS can be used in most polymer carrier systems. Internal/external lube for rigid molding and extrusion.

ADDITION LEVELS

Varies by application. Please contact technical service at 1-800-327-8649 or 330-928-5188 for more information.

FDA STATUS

STRUKTOL® TR EBS is sanctioned for use by the Food and Drug Administration (FDA) in the following section of Title 21 of the Code of Federal Regulations:

175.105 Adhesives	177.1200 Cellophane
175.300 Resinous and polymeric coatings	177.1350 Ethylene-vinyl acetate copolymer
176.170 Components of paper and paperboard in contact with aqueous and fatty foods	177.1400 Hydroxyethyl cellulose film, water-insoluble
176.180 Components of paper and paperboard in contact with dry food	177.2470 Polyoxymethylene copolymer
	177.2480 Polyoxymethylene homopolymer

(11/02/17)JMB/abw

The information herein is believed to be reliable, but is presented without guarantee or warranty, express or implied. Nothing contained herein is to be construed as a recommendation for any use which is in violation of an existing patent.