



# **STRUKTOL<sup>®</sup> TR 016**

## **PROCESSING AGENT FOR PLASTIC COMPOUNDS**

### **COMPOSITION**

A blend of fatty acid metal soap and an amide.

---

### **PROPERTIES**

Appearance	pale beads or pastilles
Dropping Point (°C)	96-108
Specific Gravity	0.98
Physiological Behavior	refer to safety data sheet
Storage Stability	at least 2 years under normal storage conditions
Packaging	25 kg. PE bags

### **RECOMMENDATIONS FOR APPLICATION**

The amide of STRUKTOL<sup>®</sup> TR 016 has sites available for hydrogen bonding, and is therefore able to act as a physical coupling agent between polymer systems and a range of filler materials. This permits STRUKTOL<sup>®</sup> TR 016 to act as an efficient blending or dispersing agent in highly filled systems, providing a more uniform and homogenous initial mix. At processing conditions, STRUKTOL<sup>®</sup> TR 016 is an effective internal lubricant for the polyolefins, PVC, PS, ABS and many of the TPO systems. Application areas recommended for STRUKTOL<sup>®</sup> TR 016 in highly-filled systems include TPEs and TPO compounds, filled olefins, flame retarded polymers and color concentrate materials. In addition, STRUKTOL<sup>®</sup> TR 016 can be useful in those standard unfilled polymers where reduced viscosity and improved flow are desirable at processing conditions. In many systems, better surface appearance and lower and more uniform mold shrinkage will be seen. Physical property losses are quite small for most compounds at normal addition levels of STRUKTOL<sup>®</sup> TR 016.

Benefits of STRUKTOL<sup>®</sup> TR 016 include:

- Improved flow at processing temperatures
- Better surface appearance
- Easier mold release in many systems
- Better dispersion of fillers and additives
- Non-blooming properties

-over-



## Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649  
Stow, Ohio 44224-0649 • www.struktol.com  
Phone (330) 928-5188 • Fax (330) 928-8726

## TECHNICAL DATA

### ADDITION LEVELS

0.25 - 1.0%

### FDA STATUS

STRUKTOL<sup>®</sup> TR 016 is sanctioned for use by the Food and Drug Administration (FDA) in a number of applications, listed in the following sections of Title 21 of the Code of Federal Regulations:

<b>173.340</b>	Defoaming agents	<b>177.2410</b>	Phenolic resins in molded articles
<b>175.105</b>	Adhesives	<b>177.2600</b>	Rubber articles intended for repeated use
<b>175.300</b>	Resinous and polymeric coatings	<b>178.2010</b>	Antioxidants and/or stabilizers for polymers
<b>175.320</b>	Resinous and polymeric coatings for polyolefin film	<b>178.3860</b>	Release agents
<b>176.170</b>	Components of paper and paperboard in contact with aqueous and fatty foods	<b>181.29</b>	Stabilizers
<b>176.200</b>	Defoaming agents used in coatings	<b>184.1229</b>	Calcium stearate
<b>176.210</b>	Defoaming agents used in the manufacture of paper and paper board		
<b>177.1200</b>	Cellophane		
<b>177.2260</b>	Filters, resin-bonded		

(05/04/05)llh

The information herein is believed to be reliable, but is presented without guarantee or warranty, express or implied. Nothing contained herein is to be construed as a recommendation for any use which is in violation of an existing patent.