



STRUKTOL[®] EF 44 A

PROCESSING ADDITIVE

COMPOSITION

Blend of fatty acid derivatives (predominantly zinc soaps).

<i>PROPERTIES</i>	<i>TYPICAL VALUES</i>
Appearance	Yellowish pastilles
Dropping Point (°C)	91-101
Specific Gravity	1.10
Zinc Content (% , max.)	9.0
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. PE bag / 2,200 lb. skid 25 kg. PE bag / 1,000 kg. skid

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] EF 44 A is a newly designed processing additive for applications in natural and synthetic rubber. Due to its selected composition comprising fatty acid derivatives with different polarities, STRUKTOL[®] EF 44 A provides excellent improvement of processing behavior for a wide range of elastomers like NR, SBR, and EPDM (except for halogenated elastomers).

STRUKTOL[®] EF 44 A is especially suited for applications in extruded compounds, but also offers advantages on transfer molding and injection molding. STRUKTOL[®] EF 44 A improves dispersion of fillers (especially mineral fillers) and has a beneficial influence on batch-to-batch uniformity. Finally, STRUKTOL[®] EF 44 A acts as a cure activator and allows for reduced dosage of stearic acid.

DOSAGE

1 - 3 phr

(05/11/2017rev1)JDC/abw