



Struktol Company of America, LLC

201 E. Steels Corners Road • P. O. Box 1649 • Stow, Ohio 44224-0649
Phone (330) 928-5188 • Fax (330) 928-0013
www.struktol.com • customerservice@struktol.com

TECHNICAL DATA

STRUKTOL[®] PE(O)-300

PROCESSING ADDITIVE FOR DISPERSION AND LUBRICATION

COMPOSITION

High molecular weight oxidized polyethylene wax.

TYPICAL PROPERTIES

Appearance	White fine granules
Dropping Point (°C)	131
Viscosity (150°C)	6000 – 14000 cps
Hardness (25°C)	<1 dmm
Bulk Density (kg/m ³)	~ 470
Specific Gravity	0.96
Physiological Behavior	Refer to safety data sheet
Storage Stability	Unlimited under normal storage conditions.
Packaging	25 kg (55 lb) bag

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] PE(O)-300 is a versatile oxidized polyethylene wax used in elastomer and plastics applications. It is particularly useful as an external lubricant for rigid and plasticized PVC. It can be used in calendered film, extruded profiles such as pipe and siding, injection molding and compounding of masterbatches and colorants

- over -



Struktol Company of America, LLC

201 E. Steels Corners Road • P. O. Box 1649 • Stow, Ohio 44224-0649
Phone (330) 928-5188 • Fax (330) 928-0013
www.struktol.com • customerservice@struktol.com

TECHNICAL DATA

DOSAGE

Injection Molding <i>(Opaque)</i>	V-HRW	0.7 – 1.5 phr	Extrusion <i>(Opaque)</i>	V-SSE	0.7 – 1.0 phr
	VLB-602 or V-PEAS	0.3 – 0.75 phr		VLB-602	0.4 – 0.8 phr
	PE(O)-300	0.07 – 0.15 phr		Calcium Stearate	0.7 – 1.0 phr
	Calcium Stearate*	0.3 – 1.0 phr		PE(O)-300	0.15 – 0.2 phr
<hr/>					
Injection Molding <i>(Clear)</i>	V-HRW	0.7 – 1.0 phr	Extrusion <i>(Clear)</i>	V-DSP	0.7 – 1.0 phr
	VLB-602 or V-PEAS	0.3 – 0.6 phr		VLB-602	0.3 – 0.6 phr
				PE(O)-300	0.1 – 0.3 phr
<hr/>					
Calendering <i>(Opaque)</i>	V-HRW	0.7 – 1.5 phr			
	VLB-602	0.5 – 0.75 phr			
	Calcium Stearate	0.3 – 0.75 phr			
	PE(O)-300	0.07 – 0.15 phr			

**Note: Reduce Calcium Stearate as much as possible for improved flow.*

FDA STATUS

STRUKTOL® PE(O)-300 is sanctioned for use by the Food and Drug Administration (FDA) listed in the following sections of Title 21 of the Code of Federal Regulations:

175.105 176.200 176.210 177.1210 177.1390 177.2600 178.3120

(03/19/2019)DS/abw

The information herein is believed to be reliable, but is presented without guarantee or warranty, express or implied. Nothing contained herein is to be construed as a recommendation for any use which is in violation of an existing patent.