



# **STRUKTOL<sup>®</sup> RP 23**

**PROCESSING ADDITIVE**

## **COMPOSITION**

Proprietary blend of fatty acid derivatives and vis-breaking technology.

<b>PROPERTIES</b>	<b>TYPICAL VALUES</b>
Appearance	White to off-white pastille
Dropping Point (°C)	77 - 87
Specific Gravity	0.98
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. bag or 800 lb. box

## **RECOMMENDATIONS FOR APPLICATION**

STRUKTOL<sup>®</sup> RP 23 is designed as a multi-functional additive for polypropylene viscosity modification, lubricating processing aid, and mold release. It also incorporates odor control technology and works well in recycle applications where polyethylene contamination exists. RP 23 is used to provide increase in melt flow index of polypropylene.

## **DOSAGE**

0.1 – 2%