



# **STRUKTOL<sup>®</sup> RP 23**

## ***PROCESSING ADDITIVE***

### **COMPOSITION**

Proprietary blend of fatty acid derivatives and vis-breaking technology.

<b><i>PROPERTIES</i></b>	<b><i>TYPICAL VALUES</i></b>
Appearance	White to off-white pastille
Dropping Point (°C)	77 - 87
Specific Gravity	0.98
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. bag or 800 lb. box

### **RECOMMENDATIONS FOR APPLICATION**

STRUKTOL<sup>®</sup> RP 23 is designed as a multi-functional additive for polypropylene viscosity modification, lubricating processing aid, and mold release. It also incorporates odor control technology and works well in recycle applications where polyethylene contamination exists. STRUKTOL<sup>®</sup> RP 23 is used to provide increase in melt flow index of polypropylene.

### **DOSAGE**

0.1 – 2%

(12/15/2017)KLH/abw