



## Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649  
Stow, Ohio 44224-0649 • www.struktol.com  
Phone (330) 928-5188 • Fax (330) 928-8726

## TECHNICAL DATA

# STRUKTOL<sup>®</sup> SCA 930 CB

### COUPLING AGENT

#### COMPOSITION

A 1:1 blend of N 330 carbon black and a bifunctional silane.

---

#### TYPICAL PROPERTIES

---

Appearance	black microbeads
Ash (% , max.)	12.8 ± 0.8
Chloride Content (% , max.)	7.2 ± 0.5
Specific Gravity (g/cm <sup>3</sup> )	1.30
Storage Stability	one year under normal storage conditions
Packaging	55 lb. box

---

#### RECOMMENDATIONS FOR APPLICATION

STRUKTOL<sup>®</sup> SCA 930 CB is used in halogenated elastomers compounded with silica, clay, or talc.

#### DOSAGE

Suggested dosage per 100 parts of filler:

For silica -           6 – 26 parts  
For clay and talc -   1 – 2 parts

(08/19/05)AAC/rca