



STRUKTOL[®] TPW 104

PROCESSING ADDITIVE

COMPOSITION

Blend of an aliphatic carboxylic acid salts and mono and diamides.

PROPERTIES	TYPICAL VALUES
Appearance	Off-white to light tan beads, pastilles or powder
Dropping Point (°C)	95 - 115
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. bag (standard)

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] TPW104 is a unique blend of lubricants designed specifically for wood fiber/flour filled polyolefins. This product will provide improved surface quality, increased output rates and a wider processing window leading to overall improved processability.

STRUKTOL[®] TPW 104 can also be used in other polyolefin compounds where improved processability or output rates are required.

DOSAGE

Typical usage levels are 2 – 6% of total compound weight.

(04/28/2016)MSF/rca