



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649 • Stow, Ohio 44224-064
Phone (330) 928-5188 • Fax (330) 928-0013
www.struktol.com • customerservice@struktol.com

TECHNICAL DATA

STRUKTOL[®] TPW 617

WPC LUBRICANT

COMPOSITION

Proprietary blend of fatty acid derivatives.

<i>PROPERTIES</i>	<i>TYPICAL VALUES</i>
Appearance	White to off-white pastille
Dropping Point (°C)	125
Specific Gravity (g/cm ³)	1.02
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions.
Packaging	25 kg. bag

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] TPW 617 is an engineered lubricant package designed specifically for wood/fiber filled polyolefins. This product will provide viscosity reduction, improved surface quality, increased throughput rates and a wider processing window leading to overall improved processability. STRUKTOL[®] TPW 617 can be used at lower loading levels than traditional lubricating products.

DOSAGE

Typical usage levels are 2 – 4% of total compound weight.

(10/17/2016)MSF/ZB/JMB/rca

The information herein is believed to be reliable, but is presented without guarantee or warranty, express or implied. Nothing contained herein is to be construed as a recommendation for any use which is in violation of an existing patent.