



STRUKTOL[®] TPW 617

WPC LUBRICANT

COMPOSITION

Proprietary blend of fatty acid derivatives.

PROPERTIES	TYPICAL VALUES
Appearance	Off-white to beige powder or pastille
Dropping Point (°C)	125
Specific Gravity (g/cm ³)	1.02
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions.
Packaging	55 lb. bag

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] TPW 617 is an engineered lubricant package designed specifically for wood/fiber filled polyolefins. This product will provide viscosity reduction, improved surface quality, increased throughput rates and a wider processing window leading to overall improved processability. STRUKTOL[®] TPW 617 can be used at lower loading levels than traditional lubricating products.

DOSAGE

Typical usage levels are 2 – 4% of total compound weight.

(10/17/2016)MSF/ZB/JMB/abw