



STRUKTOL[®] TPW 709

PROCESSING ADDITIVE

COMPOSITION

A unique proprietary blend of non-metal internal/external processing aids.

PROPERTIES	TYPICAL VALUES
Appearance	Beige to tan powder or pastille
Melting Point (°C)	123 - 137
Specific Gravity	1.00
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. PE bag

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] TPW 709 has shown excellent results in producing extruded polymer/wood composites.

DOSAGE

3 - 4% in HDPE/wood applications depending on the percent and species of wood.
1 - 2% in PP/wood formulas.

(09/05/2013)GH/ZB/rca