



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649 • Stow, Ohio 44224-064
Phone (330) 928-5188 • Fax (330) 928-0013
www.struktol.com • customerservice@struktol.com

TECHNICAL DATA

STRUKTOL[®] TR 041

PROCESSING ADDITIVE, COMPOUNDING AID

COMPOSITION

Oleochemical derivative with no metal ions.

PROPERTIES	TYPICAL VALUES
Appearance	light tan pastille or beads
Acid Value (max.)	20
Dropping Point (°C)	78 - 92
Specific Gravity	0.98
Physiological Behavior	refer to safety data sheet
Storage Stability	at least 2 years under normal storage conditions
Packaging	55 lb. PE bags

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] TR 041 is a fatty acid based additive designed to maximize the wetting to both a polar filler and a non-polar polymer. By wetting both surfaces, this material allows a quicker incorporation of additives into the polymer matrix; decreasing mixing times, melt temperatures and viscosity.

The product contains no metal soaps and may be used where these are unacceptable. The acid value is quite low, so this compound may also be used where stearic acid is a problem. Specific viscosity improvements have been seen with high impact polystyrene (HIPS).

ADDITION LEVELS

Depending on polymer and other additives, from 0.1% in PE to 1.0% or higher in HIPS.

FDA STATUS

STRUKTOL[®] TR 041 is sanctioned for use by the Food and Drug Administration (FDA) in a number of applications, listed in the following sections of Title 21 of the Code of Federal Regulations:

175.105	Adhesives	177.1580	Polycarbonate resins
175.300	Resinous and polymeric coatings	177.2420	Polyester resins, cross-linked
176.170	Components of paper and paperboard in contact with aqueous and fatty foods	178.2010	Antioxidants and/or stabilizers for polymers
176.210	Defoaming agents used in the manufacture of paper and paperboard	178.3860	Release agents
177.1200	Cellophane		

(02/17/2015)/rca

The information herein is believed to be reliable, but is presented without guarantee or warranty, express or implied. Nothing contained herein is to be construed as a recommendation for any use which is in violation of an existing patent.