



Struktol Company of America, LLC

201 E. Steels Corners Road • P. O. Box 1649 • Stow, Ohio 44224-0649
Phone (330) 928-5188 • Fax (330) 928-0013
www.struktol.com • customerservice@struktol.com

TECHNICAL DATA

STRUKTOL® TR 141

ANTI-BLOCK / SLIP AGENT / LUBRICANT / DISPERSANT / MOLD RELEASE AGENT

COMPOSITION

A saturated primary amide with no double bond.

PROPERTIES	TYPICAL VALUES
Appearance	Cream colored beads or pastilles
Amide Content (%)	95.0 - 100.0
Acid Value	9
Gardner Color	5
Melting Point (°C)	98 - 104
Specific Gravity	0.96
Physiological Behavior	Refer to safety data sheet
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. PE bags

RECOMMENDATIONS FOR APPLICATION

STRUKTOL® TR 141 stearamide is a saturated primary amide with no double bond. It blooms in an invisible monolayer for surface appearance and mold release. It can also be used for viscosity reduction.

STRUKTOL® TR 141 is relatively insoluble in water and has limited solubility in alcohol, ketones and aromatic solvents. STRUKTOL® TR 141 is used in many polymers including PVC, PS, PP, PE and elastomers. It will not interfere with peroxide cure systems in cross-linked polymer systems.

ADDITION LEVELS

Plastics	0.5 – 1.0 %
PVC	0.3 – 0.6 %
Elastomers	1 – 3 phr

FDA STATUS

STRUKTOL® TR 141 is sanctioned for use by the Food and Drug Administration (FDA) listed in the following sections of Title 21 of the Code of Federal Regulations:

175.105 177.1210 178.3910 179.45 181.28

(05/13/20)JDC/JKS/JMB/rca

The information herein is believed to be reliable, but is presented without guarantee or warranty, express or implied. Nothing contained herein is to be construed as a recommendation for any use which is in violation of an existing patent.