



Struktol Company of America

201 E. Steels Corners Road • P. O. Box 1649
Stow, Ohio 44224-0649 • www.struktol.com
Phone (330) 928-5188 • Fax (330) 928-8726

TECHNICAL DATA

STRUKTOL® TR 151-95

GLYCERYL MONOSTEARATE (GMS)

INTERNAL LUBRICANT FOR PVC

EXTERNAL LUBRICANT FOR POLYOLEFINS

COMPOSITION

Partial fatty acid esters of glycerin.

TYPICAL PROPERTIES

Appearance	Off white waxy powder
Monoglycerides (% max.)	95
Acid Value (max.)	3.0
Iodine Value (max)	3.0
Sodium Stearate (% max.)	0.1
Free Glycerol (% max.)	1.0
Melting Point (°C)	~ 68
Specific Gravity	0.94
Physiological Behavior	Refer to safety data sheet
Storage Stability	2 years in its original packaging in a dry and cool place at temperatures no more than 40°C.
Packaging	55 lb plastic bag

RECOMMENDATIONS FOR APPLICATION

STRUKTOL® TR 151-95 is a partial fatty acid ester of glycerine. It can be used as an antistatic agent in polypropylene and polyethylene. It is excellent for use in color concentrates and can be used as a lubricant/process aid in polyolefins and PVC.

STRUKTOL® TR 151-95 is recommended to improve the process of PVC extrusion, injection molding, blow molding, calendaring of sheets and films, and extrusion of profiles.

DOSAGE

Recommended dosage is:	Rigid PVC	0.5 – 1.5 phr
	Flexible PVC	0.5 – 1.0 phr
	Polyethylene PP	0.05 – 0.5 %
	LDPE	0.15 %
	HDPE	0.3 %

FDA STATUS

STRUKTOL® TR 151-95 is sanctioned for use by the Food and Drug Administration (FDA) in a number of applications, listed in the following sections of Title 21 of the Code of Federal Regulations:

175.300

175.320

177.2800

178.3130

184.1324

(4/18/12)JMB/rca

The information herein is believed to be reliable, but is presented without guarantee or warranty, express or implied. Nothing contained herein is to be construed as a recommendation for any use which is in violation of an existing patent.