



STRUKTOL[®] V-EGS

PROCESSING ADDITIVE

COMPOSITION

Ethylene glycol distearate

<i>PROPERTIES</i>	<i>TYPICAL VALUES</i>
Appearance	White to light yellow pastille or powder
Dropping point (°C)	63 - 73
Specific Gravity (g/cm ³)	.93
Storage Stability	At least 2 years under normal storage conditions
Packaging	55 lb. bag / 2,200 lb. skid 25 kg. bag / 1,000 kg. skid

RECOMMENDATIONS FOR APPLICATION

STRUKTOL[®] V-EGS is a very compatible internal/external lubricant for rigid PVC. It is particularly useful in rigid PVC extrusion such as window, siding and other profiles.

STRUKTOL[®] V-EGS is also good in injection molding formulations.

DOSAGE

Typical dosage is between 0.5 – 1.5 phr

(04/04/2016Rev1)JDC/abw